

Slump Test

It measures the consistency of a concrete mix or its stiffness. A conical mould is filled with fresh concrete in 3 stages & rammed with a standard rod. The mould is lifted without disturbing the cone. The subsidence of the concrete from the height of the cone is measured to the nearest 5cm. The testing can also be done in the presence of customer at our in house laboratory .

