





## Wheatland Tube

## Providing Quality Products and Service for Over 130 Years

Wheatland Tube is one of the largest high-volume national manufacturers of fence framework products.

We are the only manufacturer that produces the full range of pipe and tubing for all fence applications. Our Regular Grade Schedule 40 pipe was used as the original specification for all security and industrial fence framework. Today, we supply the broadest line of fence framework in the industry for projects involving high-security, industrial, commercial and residential applications. Our products are highly recognized for their superior strength, quality, and unparalleled range of sizes and protective coatings. We stock full inventories and we're the only supplier that offers mixed loads shipped on the same truck, providing our customers with additional savings on freight and the ability to consolidate purchase orders, invoices and payments.

Wheatland Tube will certify that all Wheatland fence framework is manufactured in the USA and is in compliance with applicable local, state and federal specifications. "MADE IN USA" is displayed on each length of fence pipe and tube. Made & Melted in America, Wheatland Tube's steel pipe and tube satisfy the strictest American Made, Made in America and Buy American Standards.



#### Galvanizing

Wheatland Tube is unique in that it can offer both hot-dipped and in-line galvanized products that meet ASTM standards.



#### Recyclable

The steel used to produce Wheatland's fence framework contains recycled steel, which is the most recycled material in the world.

The tube products manufactured by Wheatland Tube are produced from approximately 25-85% recycled steel. The amount can vary depending on the steel producer. Of the 25-85% recycled steel, approximately 30% is post-industrial and 70% is post-consumer — depending on fluctuating scrap prices. The American Iron and Steel Institute (AISI) states, "Steel's recycling rate of 66% is far higher than that of any other material, capturing twice as much tonnage as all other materials combined."



#### **Color Coatings**

Wheatland's polyester
TGIC powder-coated
WT-ColorCoat (per ASTM
F1043 in dark green or
black per ASTM F934)
is applied over the
galvanized exterior coatings
to provide additional
corrosion protection.
WT-ColorCoat is available
on WT-40, WT-30, WT-20,
WT-15, residential tubing
and squares.



#### **Value-added Services**

Wheatland's goal is to continually work with our customers to educate them on our products and services and follow up to make sure that we are meeting their needs. Our customer service team is committed to building long-term partnerships that are based on high-quality deliverables. Our highly qualified technical team allows us to offer you the expertise in providing solutions for projects of various sizes. We make it our business to understand your business and your priorities. Wheatland offers the most extensive size range of any fence framework manufacturer, including swaged ends. We can ship all of our fence products on a single truckload, reducing deliveries and associated costs.

# High-security, Security and Industrial Fence Framework

#### Schedule 40 per ASTM F1083, WT-40 per ASTM F1043

**Applications** – Prisons, military and secure government facilities, highways, bridge fencing, utility and water treatment plants, schools, public play and ball fields, border fence, chemical plants, sea ports, airports, framework and supports for solar panels – basically unlimited applications.

#### Schedule 40 per ASTM F1083

Wheatland F1083 is the original specified fence framework used for commercial, industrial and high-security applications. Wheatland is the leading supplier of ASTM F1083 full-weight Schedule 40 domestic fence framework. Wheatland manufactures all F1083 grades; Regular Grade 30,000 psi, High Strength 50,000 psi and Schedule 80. When the specification requires Schedule 40 pipe, Wheatland's F1083 is the clear choice. Our ISO 9001 certified CW facility produces the finest Schedule 40 products in the world and is supported by over 130 years of experience delivering prompt, knowledgeable and personalized service.

- Meets or exceeds the requirements of ASTM F1083
- Meets or exceeds the requirements of ASTM F1043, Group 1A
- Full-weight Schedule 40 wall thickness
- Pure zinc hot-dip galvanized 1.8 oz./ft² outside, and 1.8 oz./ft² inside (2.0 oz./ft² available)
- Conversion coating inside and outside for additional protection
- The only Schedule 40 pipe coated with virtually lead-free galvanizing
- Most extensive size range of any fence framework product, 1% "-8 % " OD

#### Certification

Wheatland Tube will certify that all Wheatland F1083 fence pipe is manufactured in the USA and is in compliance with applicable local, state and federal specifications. "WHEATLAND USA ASTM F1083" is proudly displayed on each length of F1083 pipe.

#### **Specifying Agencies**

- American Association of State Highway and Transportation Officials (AASHTO) M181—Grade 1
- Federal specifications RR-F-191/2E and RR-F-191/3E
- U.S. Army Corps of Engineers UFGS-32 31 13
- Department of the Navy
- Department of Transportation
- Federal Aviation Administration AC 150/5370-10 Item 162
- U.S. Department of Justice Federal Bureau of Prisons
- ASTM Specification F1043, Group 1A, Standard Specification for Strength and Protective Coatings
- American Institute of Architects (AIA) MasterSpec®
- ASTM Specification F1083



### F1083 Tables

## ASTM F1083 Regular Grade 30,000 PSI Yield Schedule 40 Pipe — Dimensions and Strength Characteristics

FENCE INDUSTRY	DECIM EQUIV		PIPE \		WEI	GHT	SECT MOD		x	MIN. Y		=	MAX. BENDING MOMENT	CALCULATI	ED LOAD	(LBS.)
														10' Free	Canti	lever
OD	in.	(mm)	in.	(mm)	lb./ft.	(kg/m)	in.³	(mm³)	x	psi	(MPa)	=	lb./in.	Supported	4'	6'
13/8"	1.315	33.40	0.133	3.38	1.68	2.50	0.1328	3.37	Х	30000	205	=	3985	133	83	55
15/8"	1.660	42.16	0.140	3.56	2.27	3.38	0.2346	5.96	Х	30000	205	=	7038	235	147	98
17⁄8"	1.900	48.26	0.145	3.68	2.72	4.05	0.3262	8.29	х	30000	205	=	9786	326	204	136
23/8"	2.375	60.33	0.154	3.91	3.65	5.43	0.5606	14.24	х	30000	205	=	16819	561	350	234
2 1/8"	2.875	73.03	0.203	5.16	5.80	8.62	1.0640	27.03	X	30000	205	=	31921	1064	665	443
3 1/2"	3.500	88.90	0.216	5.49	7.58	11.28	1.7241	43.79	Х	30000	205	=	51723	1724	1078	718
4"	4.000	101.60	0.226	5.74	9.12	13.56	2.3939	60.80	х	30000	205	=	71816	2394	1496	997
41/2"	4.500	114.30	0.237	6.02	10.80	16.07	3.2145	81.65	Х	30000	205	=	96435	3214	2009	1399
*5 %16"	5.563	141.30	0.258	6.55	14.63	21.77	5.4511	138.46	Х	35000	240	=	190789	6359	3975	2650
*6 5/8"	6.625	168.28	0.280	7.11	18.99	28.23	8.4958	215.79	х	35000	240	=	297353	9912	6195	4130
*8 5/8"	8.625	219.08	0.322	8.18	28.58	42.49	16.8091	426.95	х	35000	240	=	588319	19610	12257	8171

<sup>\*</sup>Manufactured to ASTM A53 specifications; exceeds F1083 requirements.

## ASTM F1083 High Strength Grade 50,000 PSI Yield Schedule 40 Pipe — Dimensions and Strength Characteristics

FENCE INDUSTRY	DECIM EQUIV		PIPE \		WEI	GHT	SECT		x	MIN. Y		=	MAX. BENDING MOMENT	CALCULATI	ED LOAD	(LBS.)
														10' Free	Canti	lever
OD	in.	(mm)	in.	(mm)	lb./ft.	(kg/m)	in.³	(mm³)	x	psi	(MPa)	=	lb./in.	Supported	6'	15'
15⁄8"	1.660	42.16	0.140	3.56	2.27	3.38	0.2346	5.96	Х	50000	345	=	11730	392	163	65
17⁄8"	1.900	48.26	0.145	3.68	2.72	4.05	0.3262	8.29	х	50000	345	=	16310	543	227	91
23/8"	2.375	60.33	0.154	3.91	3.65	5.43	0.5606	14.24	х	50000	345	=	28030	935	389	156
2 1/8"	2.875	73.03	0.203	5.16	5.80	8.62	1.0640	27.03	х	50000	345	=	53200	1773	739	296
31/2"	3.500	88.90	0.216	5.49	7.58	11.28	1.7241	43.79	х	50000	345	=	86205	2873	1197	479
41/2"	4.500	114.30	0.237	6.02	10.80	16.07	3.2145	81.65	х	50000	345	=	160725	5357	2232	893
5 %16"	5.563	141.30	0.258	6.55	14.63	21.77	5.4511	138.46	х	50000	345	=	272555	9085	3785	1514
6 5/8"	6.625	168.28	0.280	7.11	18.99	28.23	8.4958	215.79	Х	50000	345	=	424790	14160	5900	2360
8 5/8"	8.625	219.08	0.322	8.18	28.58	42.49	16.8091	426.95	х	50000	345	=	840455	28015	11673	4669

Please contact Fence Sales for mill run schedule. Minimum order quantities may be required.

Specifications, illustrated material and descriptions are accurate as known at time of publication and are subject to change without notice.

## ASTM F1083 Regular Grade 30,000 PSI Yield Schedule 80 Pipe — Dimensions and Strength Characteristics

FENCE INDUSTRY	DECIM EQUIV		PIPE \		WEI	GHT	SECT MOD		x	MIN. Y		=	MAX. BENDING MOMENT	CALCULATE	ED LOAD	(LBS.)
														10' Free	Canti	lever
OD	in.	(mm)	in.	(mm)	lb./ft.	(kg/m)	in.³	(mm³)	x	psi	(MPa)	=	lb./in.	Supported	4'	6'
13/8"	1.315	33.40	0.179	4.55	2.17	3.23	0.1606	4.08	Х	30000	205	=	4819	161	100	67
15/8"	1.660	42.16	0.191	4.85	3.00	4.46	0.2913	7.40	х	30000	205	=	8739	291	182	121
1 1/8"	1.900	48.26	0.200	5.08	3.63	5.40	0.4118	10.46	х	30000	205	=	12354	412	257	172
23/8"	2.375	60.33	0.218	5.54	5.03	7.49	0.7309	18.56	х	30000	205	=	21926	731	457	305
2 1/8"	2.875	73.03	0.276	7.01	7.67	11.41	1.3386	34.00	x	30000	205	=	40158	1339	837	558
3 1/2"	3.500	88.90	0.300	7.62	10.26	15.27	2.2253	56.52	х	30000	205	=	66760	2225	1391	927
4"	4.000	101.60	0.318	8.08	12.52	18.63	3.1401	79.76	х	30000	205	=	94202	3140	1963	1308
4 1/2"	4.500	114.30	0.337	8.56	15.00	22.32	4.2713	108.49	x	30000	205	=	128140	4271	2670	1780

Specifications, illustrated material and descriptions are accurate as known at time of publication and are subject to change without notice.




## WT-40 per ASTM F1043, Group 1C

Wheatland Tube will certify that all Wheatland WT-40 pipe is manufactured in the USA and is in compliance with applicable local, state and federal specifications. "WT-40 MADE IN USA" is proudly displayed on each length of WT-40 pipe.

#### **High-strength Spec Fence Framework**

The strength and corrosion characteristics of Wheatland WT-40 fence pipe have been tested, documented and certified by independent testing agencies to ensure complete compliance with ASTM F1043, Group IC, and AASHTO M181. Wheatland WT-40 fence framework meets or exceeds the most demanding specifications and codes imposed by private, independent and government agencies.



#### **Materials**

- **1. Steel** Steel strip used in the manufacture of Wheatland WT-40 fence pipe shall conform to ASTM A1011 and will meet or exceed all performance criteria set forth in this standard specification.
- **2. Zinc** Zinc used in Wheatland WT-40 fence pipe shall conform to ASTM B6. Galvanizing shall be continuous hot-dipped on OD.
- **3. Conversion Coating** An intermediate conversion coating shall be applied in-line over the continuous hot-dip galvanizing coating to inhibit white rust and enhance corrosion resistance.
- **4. Clear Polymer Coating** A clear polymer coating shall be applied over the intermediate conversion coating. This polymer coating provides a smooth, lustrous protective finish.
- **5. Heat-set Internal Coating** A heat-set zinc-rich ID coating shall have a minimum zinc loading of 90%.

#### **Weight of Coatings**

- Zinc Weight of zinc shall be 1.0 oz./ft.<sup>2</sup> +/- 0.1 oz./ft.<sup>2</sup> and shall be determined by the method described in ASTM A90.
- 2. Intermediate Coating Intermediate conversion coatings shall be 30 micrograms/in.<sup>2</sup> +/- 10 micrograms/in.<sup>2</sup> and shall be determined by a strip and weigh method utilizing an atomic absorption spectrophotometer or X-ray fluorescence spectrograph.
- 3. Polymer Coating Thickness of the clear polymer coating shall be 0.5 mils +/- 0.2 mils and shall be determined by measurement with a suitable magnetic or eddy current coating thickness tester.

#### **Strength Characteristics**

- 1. Load Strength The strength of line, end, corner and pull posts shall be determined by the use of 4' or 6' cantilevered bend test. The top rail shall be determined by a 10' free-supported beam test.
- 2. Bending Moment Pipe strength may be determined via the alternative method of calculating bending moment. (See table.) Conformance can be demonstrated by measuring the yield strength multiplied by the section modulus. The yield strength shall be determined according to the methods described in ASTM E8. For materials under this specification, the 0.2 offset method shall be used in determining yield strength.



#### **Corrosion Resistance**

#### 1. Salt Spray

- a. Exterior Surface The exterior clear polymer coating shall have a demonstrated ability to resist 1,000 hours or more of exposure to salt fog with a maximum of 5% red rust. Tests shall be conducted in accordance with ASTM B117.
- b. Interior Surface The interior zinc-rich surface coating shall withstand no less than 650 hours of exposure to salt fog with a maximum of 5% red rust. Tests shall be conducted in accordance with ASTM B117.
- 2. Humidity The exterior clear polymer coating of Wheatland WT-40 fence pipe shall resist 500 hours of exposure to 100% relative humidity without signs of blistering or peeling. Tests shall be performed in accordance with ASTM D4585 (D2247).
- **3. Weatherometer** The clear polymer coating of Wheatland WT-40 fence pipe shall resist failure for no less than 500 hours at a black panel temperature of no less than 145° F. Tests shall be performed in accordance with ASTM G155 Xenon Type BH apparatus (formerly G26) or ASTM G153 Carbon ArcType HH apparatus (formerly G23).

#### **Specifying Agencies**

- American Association of State Highway and Transportation Officials (AASHTO) M181—Grade 2
- Federal specifications RR-F-191/2E and RR-F-191/3E
- U.S. Army Corps of Engineers UFGS-32 31 13
- Department of the Navy
- Federal Highway Administration
- Federal Aviation Administration AC 150/5370-10 Item 162
- U.S. Department of Justice Federal Bureau of Prisons
- ASTM Specification F1043, Group IC, Standard Specification for Strength and Protective Coatings on Steel Industrial Chain Link Fence Framework
- American Institute of Architects (AIA) MasterSpec

### **WT-40 Dimensions and Strength Characteristics**


FENCE INDUSTRY		AL OD ALENT	PIPE \		WEI	GHT	SECT MOD		x	MIN. Y		=	MAX. BENDING MOMENT	CALCULATI	ED LOAD	) (LBS.)
														10' Free		ilever
OD	in.	(mm)	in.	(mm)	lb./ft.	(kg/m)	in.³	(mm³)	X	psi	(MPa)	=	lb./in.	Supported	4'	6'
15⁄8"	1.660	42.16	0.111	2.82	1.84	2.74	0.1962	4.98	х	50000	345	=	9810	327	204	136
17⁄8"	1.900	48.26	0.120	3.05	2.28	3.39	0.2810	7.14	х	50000	345	=	14050	468	293	195
2 3/8"	2.375	60.33	0.130	3.30	3.12	4.64	0.4881	12.40	Х	50000	345	=	24405	814	508	339
2 1/8"	2.875	73.03	0.160	4.06	4.64	6.91	0.8778	22.30	х	50000	345	=	43890	1463	914	610
3 1/2"	3.500	88.90	0.160	4.06	5.71	8.50	1.3408	34.06	х	50000	345	=	67042	2235	1397	931
4"	4.000	101.60	0.160	4.06	6.56	9.76	1.7820	45.26	х	50000	345	=	89098	2970	1856	1237

# Industrial Fence Framework Applications

#### WT-30 per ASTM F1043, Group IV

WT-30 is produced in compliance with ASTM F1043, Group IV. Wheatland's state-of-theart in-line ERW manufacturing process produces a uniform triple layer of OD protection against corrosion. The application of the highest-quality zinc is followed by a conversion coating and top-coated with clear polymer coating for superior corrosion resistance.

- Exceeds the internal and external coating requirements of F1043
- Minimum yield strength of 50,000 psi
- Solution for challenging industrial and commercial fence projects





## **WT-30 Dimensions and Strength Characteristics**

FENCE INDUSTRY	DECIM EQUIV		PIPE V		WEI	GHT	SECT MODE		x	MIN. Y		=	MAX. BENDING MOMENT	CALCULATI	ED LOAD	(LBS.)
														10' Free	Canti	ilever
OD	in.	(mm)	in.	(mm)	lb./ft.	(kg/m)	in.³	(mm³)	x	psi	(MPa)	=	lb./in.	Supported	4'	6'
15⁄8"	1.660	42.16	0.095	2.41	1.59	2.36	0.1730	4.39	X	50000	345	=	8650	288	180	120
17⁄8"	1.900	48.26	0.105	2.66	2.01	2.99	0.2519	6.40	Х	50000	345	=	12595	420	262	175
2 3/8"	2.375	60.33	0.115	2.92	2.78	4.13	0.4402	11.18	Х	50000	345	=	22010	734	458	306
2 1/8"	2.875	73.03	0.125	3.18	3.66	5.44	0.7116	18.07	Х	50000	345	=	35580	1186	741	494
3 1/2"	3.500	88.90	0.145	3.68	5.20	7.74	1.2310	31.27	Х	50000	345	=	61550	2052	1282	855
4"	4.000	101.60	0.145	3.68	5.98	8.90	1.6338	41.50	х	50000	345	=	81690	2723	1702	1135

WT-30 meets or exceeds ASTM F1043, Group IV.

Specifications, illustrated material and descriptions are accurate as known at time of publication and are subject to change without notice.



### **Commercial Fence Framework**

#### WT-20 and WT-15

**Applications** — Manufacturing plants, warehouse centers, commercial centers, office buildings, day care centers, shopping centers, private parks, residential developments, private play areas, high-end residential, private schools, interior warehouse fencing, auto dealerships, dog runs, parking lots and a wide variety of other applications.

#### **WT-20**

Wheatland WT-20 fence framework is the ideal pipe for industrial and commercial jobs. Wheatland's advanced in-line coating process ensures the highest standard of corrosion resistance. WT-20 high-strength steel guarantees performance to meet your customers' needs. You can count on it!

#### Certification

Wheatland Tube will certify that all Wheatland WT-20 pipe is manufactured in the USA.

"WT-20 MADE IN USA" is proudly displayed on each length of WT-20 pipe.

### **WT-20 Performance Specifications**

Strength	50,000 psi yield strength (minimum) certification
Appearance	Permanent smooth, high-shine, clear polymer-coated galvanized finish
Durability	Meets or exceeds the following specifications: ASTM B117 300-hour salt fog test ASTM D1499 500-hour weathering test ASTM D2247 500-hour humidity test
Availability	Available in cut posts, 21' and 24' lengths Special lengths up to 42' upon request for fast-track shipment

## **WT-20 Dimensions and Strength Characteristics**

ENCE DUSTRY	DECIM EQUIV		PIPE V		WEI	GHT	SECT MODE		X	MIN. Y		=	MAX. BENDING MOMENT	CALCULATE	ED LOAD	(LBS.)
OD	in.	(mm)	in.	(mm)	lb./ft.	(kg/m)	in.³	(mm³)	х	psi	(MPa)	_	lb./in.	10' Free Supported	Canti 4'	lever 6'
OD	111.	(111111)	111.	(111111)	ID./ IL.	(kg/III)	111	(111111-)	X	psi	(MPa)	-	ID./ III.	Supported	4	•
13/8"	1.315	33.40	0.080	2.03	1.06	1.57	0.0904	2.30	×	50000	345	=	4520	151	94	63
15⁄8"	1.660	42.16	0.085	2.16	1.43	2.13	0.1576	4.00	Х	50000	345	=	7880	263	164	109
11/8"	1.900	48.26	0.090	2.29	1.74	2.59	0.2212	5.62	Х	50000	345	=	11060	369	230	154
23/8"	2.375	60.33	0.095	2.41	2.32	3.45	0.3730	9.47	х	50000	345	=	18650	622	389	259
2 1/8"	2.875	73.03	0.110	2.79	3.25	4.84	0.6362	16.16	Х	50000	345	=	31810	1060	663	442

Specifications, illustrated material and descriptions are accurate as known at time of publication and are subject to change without notice.



#### WT-15

Wheatland WT-15 fence framework is the ideal pipe for light industrial and commercial jobs. Wheatland's advanced in-line coating process ensures the highest standard of corrosion resistance. WT-15 high-strength steel is guaranteed to meet or exceed your customers' needs. You can count on it!

#### Certification

Wheatland Tube will certify that all Wheatland WT-15 pipe is manufactured in the USA.

"WT-15 MADE IN USA" is proudly displayed on each length of WT-15 pipe.

## **WT-15 Performance Specifications**

Strength	50,000 psi yield strength (minimum) certification
Appearance	Permanent smooth, high-shine, clear polymer-coated galvanized finish
Durability	Meets or exceeds the following specifications: ASTM B117 300-hour salt fog test ASTM D1499 500-hour weathering test ASTM D2247 500-hour humidity test
Availability	Available in cut posts, 21' and 24' lengths Special lengths upon request for fast-track shipment

## **WT-15 Dimensions and Strength Characteristics**

FENCE DUSTRY	DECIM EQUIV	AL OD ALENT	PIPE \		WEI	GHT	SECT MOD		X	MIN. Y		=	MAX. BENDING MOMENT	CALCULATE	ED LOAD	(LBS.)
OD	in.	(mm)	in.	(mm)	lb./ft.	(kg/m)	in.³	(mm³)	x	psi	(MPa)	_	lb./in.	10' Free Supported	Canti 4'	ilever 6'
13/8"	1.315	33.40	0.072	1.83	0.96	1.42	0.0829	2.11	х	50000	345	=	4145	138	86	58
15⁄8"	1.660	42.16	0.072	1.83	1.22	1.82	0.1367	3.47	х	50000	345	=	6835	228	142	95
17⁄8"	1.900	48.26	0.072	1.83	1.41	2.09	0.1921	4.63	х	50000	345	=	9605	320	200	133
23/8"	2.375	60.33	0.072	1.83	1.77	2.63	0.2911	7.39	х	50000	345	=	14555	485	303	202

WT-15 is available in standard lengths of 21' and 24'. Special lengths up to 42' are available upon request.

Specifications, illustrated material and descriptions are accurate as known at time of publication and are subject to change without notice.



## **Residential Fence Framework**

**Applications** — Single-family residential, pool fencing and temporary fencing for limited pedestrian control and to block public access to non-secure sites.

Wheatland manufactures a full line of high-strength, light-wall steel tubing with a triple exterior coating — hot-dip zinc, conversion coating and a clear coat. The interior of the tubing is protected by a zinc-rich coating. It's available in diameters from 1%" to 2%" OD and in wall thicknesses of 0.065", 0.055" and 0.047".

### **Residential Fence Framework Chart**

#### **Size and Dimension Range**

PRODUCT	FENCE OD	DECIMAL EQUIVALENT	WALL THICKNESS	GAUGE	WEIGHT (LBS./FT.)
Residential	13/8	1.315	0.047	18	0.64
Residential	13/8	1.315	0.055	17	0.74
Residential	13/8	1.315	0.065	16	0.87
WT-15	13/8	1.315	0.072	15	0.96
Residential	15%	1.660	0.047	18	0.81
Residential	15⁄8	1.660	0.055	17	0.94
Residential	15⁄8	1.660	0.065	16	1.11
WT-15	15⁄8	1.660	0.072	15	1.22
Residential	11/8	1.900	0.047	18	0.93
Residential	11/8	1.900	0.055	17	1.08
Residential	11/8	1.900	0.065	16	1.27
WT-15	11/8	1.900	0.072	15	1.41
Residential	2 <sup>3</sup> / <sub>8</sub>	2.375	0.047	18	1.17
Residential	2 <sup>3</sup> / <sub>8</sub>	2.375	0.055	17	1.36
Residential	2 <sup>3</sup> / <sub>8</sub>	2.375	0.065	16	1.60
WT-15	23/8	2.375	0.072	15	1.77

## **Square and Rectangular Tubing**

#### **Galvanized Steel Tubing for Ornamental Fencing and Custom Framework Applications**

**Applications** — Manufactured ornamental panels, posts, railings, gates, custom fence and general decorative applications.


Wheatland's square sections are manufactured in accordance with ASTM F2589. All shapes receive a triple exterior coating that consists of a hot-dip zinc coating, conversion coating and clear coat. The interior is protected with a zinc-rich coating.

Wheatland tubing is manufactured with the highest-quality steel and forming processes to ensure strength, beauty and construction integrity. Wheatland's galvanized square and rectangle products are protected with a clear polymer coating that provides excellent adhesion properties for most paint and powder coatings. Painting or powder coating over Wheatland's galvanized steel tubing provides greater corrosion resistance than coating over non-galvanized steel tubing.

Wheatland's square and rectangle products are conveniently available at our Chicago facilities for distribution in mixed truckload shipments with our other residential, commercial and industrial products.

#### Wheatland Square Tube Products Are Manufactured:

- With steel strip conforming to ASTM A1008 or A1011
- With zinc conforming to ASTM B6 high-grade and special high-grade zinc



## **Square and Rectangular Tubing**

SHAPE	SIZE	GAUGE	PIECES/BUNDLE	LENGTH
Square	0.625"	18	242	24'
Square	0.750"	18	180	24'
Square	0.750"	16	180	24'
Square	1.00"	16	180	24'
Square	1.25"	16	144	24'
Square	1.50"	16	81	24'
Square	2.00"	16	25	24'
Square	2.00"	14	25	24'
Square	2.50 "	14	25	24'
Square	2.50 "	12	25	24'
Square	3.00"	14	25	24'
Square	3.00"	11	25	24'
Square	4.00"	13	16	24'
Square	4.00"	11	16	24'

Rectangle sizes from 0.75" x 1.5" through 2" x 4" are available. Contact us for stock availability on these and special sizes and lengths.

Other sizes are available upon request. If you require larger sizes, heavy wall or hollow structural sections, visit our sister company, Atlas Tube (atlastube.com).

Specifications, illustrated material and descriptions are accurate as known at time of publication and are subject to change without notice. All tubular products are produced in accordance with ASTM A513 and ASTM A500. In-line galvanized coatings produced in accordance with ASTM 1057.



700 South Dock Street Sharon, PA 16146 800.257.8182 info@wheatland.com

wheatland.com



#### **Corporate Office**

227 West Monroe Street Suite 2600 Chicago, IL 60606

312.275.1600 info@zekelman.com zekelman.com

#### **About Wheatland Tube**

Wheatland Tube, a division of Zekelman Industries, produces a wide range of steel tubular products, including standard steel pipe, galvanized mechanical tubing, fence framework, fire sprinkler pipe, electrical conduit, elbows, couplings and nipples.

For more information, contact Wheatland Tube at:

800.257.8182 or info@wheatland.com

Or, visit our website at wheatland.com

Follow us on:



linkedin.com/company/zekelman-industries



wheatland.com/blog